



REF. 301001 BOX 10 kg AVERAGE.





JOSPER CHARCOAL -HEXAGONAL BRIQUETTE

TECHNICAL DATA SHEET		
Box weight (average)	10 kg	22,04 lb
Fixed carbon	≈ 80 %	
Ashes	< 5 %	
Volatile solids	< 5 %	
Humidity	< 5 %	
Spark	No	
Performance	> 8000 Kcal/kg	>14390.3 btu/lb
Wood type	Hardwoods	
Morphology	Stick, Hexagon	
Density	1200 - 1300 kg/m³	79 - 81 lb/ft³
Recommended use	Josper Charcoal Oven Josper Charcoal Grill	

FIRE UP METHOD

LUMIX fire lighters should be used for the charcoal ignition points.



Never use flammable liquids during the fire up process. They are very dangerous.



HEXAGONAL BRIQUETTE

The briquette main characteristic is that it is made of sawdust from compacted hardwoods. Posteriously it is dried at 10% humidity degree and pressed as a briquette. No type of binder is used, since the humidity and wood's own lignin work as a natural glue making this type of charcoal specially indicated to work on Robatas. Its compacted embers and slow burning provides a better calorific and work performance.








Ed.02.2020 - Josper reserves the right to make modifications to catalogues, pricelists and promotional material according to the development and improvements applied to its equipment.













www.jospergrill.com